# Electrafil® PA6/6 GF20 AS BK

## Polyamide 66

## **Techmer Engineered Solutions**

#### Message:

Electrafil® PA6/6 GF20 AS BK is a Polyamide 66 (Nylon 66) product filled with 20% glass fiber. It can be processed by injection molding and is available in North America. Characteristics include: Antistatic Heat Stabilizer Lubricated

General Information				
Filler / Reinforcement	Glass Fiber,20% Filler by Weight			
Additive	Antistatic			
	Heat Stabilizer			
	Lubricant			
Features	Antistatic			
	Heat Stabilized			
	Lubricated			
Appearance	Black			
Forms	Pellets			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.23	g/cm³	ASTM D792	
Molding Shrinkage - Flow (3.18 mm)	0.40	%	ASTM D955	
Water Absorption (24 hr)	0.80	%	ASTM D570	
Hardness	Nominal Value	Unit	Test Method	
Rockwell Hardness (R-Scale)	112		ASTM D785	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	96.5	MPa	ASTM D638	
Tensile Elongation (Break)	4.5	%	ASTM D638	
Flexural Modulus	5520	MPa	ASTM D790	
Flexural Strength	159	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (23°C, 3.18 mm)	91	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load			ASTM D648	
0.45 MPa, Unannealed	260	°C		
1.8 MPa, Unannealed	227	°C		
CLTE - Flow	1.8E-5	cm/cm/°C	ASTM D696	

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+10 to 1.0E+12	ohms	ASTM D257
Volume Resistivity	1.0E+10 to 1.0E+12	ohms•cm	ASTM D257
Dielectric Strength <sup>1</sup>	18	kV/mm	ASTM D149
NOTE			
1.	Method A (Short-Time)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

