

TITANPRO® 6331

Polypropylene Homopolymer
Lotte Chemical Titan (M) Sdn. Bhd.

Message:

Polypropylene homopolymer. The base resin meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520(a)(1)(i) and (c)1.1a. The adjuvant meet their respective FDA regulations and 21 CFR 177.1520(b). In summary, this resin meets the FDS criteria covering safe use of polyolefin articles and component of articles intended for food contact use. TSCA Registry: CAS# 9003-07-0

APPLICATIONS:

Closures, housewares, toys, games, pill boxes, containers, healthcare devices, syringe barrel, pen cap and pen body.

Characteristics:

Good processability, High stiffness, Good heat deflection temperature, Microwaveable for food reheating purposes.

General Information			
Features	General Purpose		
	Good Processability		
	High Stiffness		
	Homopolymer		
Uses	Closures		
	Containers		
	General Purpose		
	Household Goods		
	Medical/Healthcare Applications		
	Toys		
	Writing Instruments		
Agency Ratings	FDA 21 CFR 177.1520(a) 1 (i)		
	FDA 21 CFR 177.1520(b)		
	FDA 21 CFR 177.1520(c) 1.1a		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	14	g/10 min	ASTM D1238
Water Absorption (24 hr)	0.020	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	97		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	35.3	MPa	ASTM D638
Tensile Elongation (Yield)	10	%	ASTM D638
Flexural Modulus	1720	MPa	ASTM D790B

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	25	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	99.0	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

