

MAJORIS G209 BLACK 8229

Polypropylene

AD majoris

Message:

MAJORIS G209 BLACK 8229 is a special long glass fibre reinforced polypropylene grade, for injection moulding and extrusion. The long glass fibres, chemically coupled to the polypropylene matrix, are providing with outstanding mechanical properties.

This product is laser printable.

MAJORIS G209 BLACK 8229 is available only in black.

APPLICATIONS

MAJORIS G209 BLACK 8229 is intended for injection moulding of highly demanding technical applications.

The excellent properties of MAJORIS G209 BLACK 8229 make it suitable for:

Electrical components, automotive parts, interior, exterior and under the bonnet, structural furniture parts, load bearing, demanding components for various engineering sectors.

MAJORIS G209 BLACK 8229 can, in many of these applications, substitute other engineering plastics or metal alloys.

General Information	
Filler / Reinforcement	Long glass fiber
Additive	heat stabilizer
Features	Chemical coupling
	Laser marking
	Recyclable materials
	Heat resistance, high
	Thermal Stability
Uses	Electrical components
	Furniture
	Metal substitution
	Parts under the hood of a car
	Car interior parts
	Automotive exterior parts
Appearance	Black
Forms	Particle
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm ³	ISO 1183
Molding Shrinkage	0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4500	MPa	ISO 527-2/1
Tensile Stress (Break)	80.0	MPa	ISO 527-2/50
Tensile Strain (Break)	3.0	%	ISO 527-2/50

Flexural Modulus	4600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	13	kJ/m ²	ISO 179/1eA
23°C	10	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	159	°C	ISO 75-2/B
Vicat Softening Temperature	142	°C	ISO 306/B
CLTE - Flow			ASTM D696
-30°C	5.9E-5	cm/cm/°C	ASTM D696
23°C	5.4E-5	cm/cm/°C	ASTM D696
Injection	Nominal Value	Unit	
Rear Temperature	230 - 250	°C	
Processing (Melt) Temp	250 - 280	°C	
Mold Temperature	80.0 - 100	°C	
Injection Pressure	30.0 - 60.0	MPa	
Injection Rate	Slow		
Screw Speed	30 - 150	rpm	
Injection instructions			

Holding pressure: 50 to 70% of the injection pressure Back pressure: as low as possible, 0 to 10% Holding time: as long as practical

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

