

LNP™ THERMOCOMP™ DF003E compound

Polycarbonate
SABIC Innovative Plastics

Message:

LNP THERMOCOMP DF003E is a compound based on Polycarbonate resin containing 15% Glass Fiber. Added features of this material include: Easy Molding.

Also known as: LNP* THERMOCOMP* Compound DF-1003 EM

Product reorder name: DF003E

General Information			
UL YellowCard	E121562-101282746	E121562-101344533	
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Features	Good Moldability		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.40 to 0.60	%	ASTM D955
Across Flow : 24 hr	0.50 to 0.70	%	ASTM D955
Across Flow : 24 hr	0.63	%	ISO 294-4
Flow : 24 hr	0.54	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	4830	MPa	ASTM D638
--	4750	MPa	ISO 527-2/1
Tensile Strength			
Yield	82.7	MPa	ASTM D638
Yield	82.0	MPa	ISO 527-2
Break	77.2	MPa	ASTM D638
Break	78.0	MPa	ISO 527-2
Tensile Elongation			
Yield	3.2	%	ASTM D638
Yield	3.3	%	ISO 527-2
Break	5.0	%	ASTM D638
Break	4.4	%	ISO 527-2
Flexural Modulus			
--	4140	MPa	ASTM D790
--	4300	MPa	ISO 178
Flexural Stress	130	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact			
23°C	80	J/m	ASTM D256
23°C ²	7.4	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	910	J/m	ASTM D4812
23°C ³	56	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	20.4	J	ASTM D3763
--	6.70	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	144	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁴	144	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	139	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	139	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	6.8E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Transverse : -40 to 40°C	3.4E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	3.5E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	293 to 304	°C	
Middle Temperature	310 to 321	°C	
Front Temperature	321 to 332	°C	
Processing (Melt) Temp	304 to 327	°C	
Mold Temperature	82.2 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

