# Thermoset Plastics UR-127

#### Polyurethane

Demold Time (25°C)

Thermoset, Lord Chemical Products

#### Message:

Thermoset Plastics UR-127 is a Polyurethane material. It is available in North America for casting. Important attributes of Thermoset Plastics UR-127 are:
High Hardness
Low Viscosity

General Information			
Features	High Hardness		
	Low Viscosity		
Appearance	White		
Forms	Pellets		
Processing Method	Casting		
Physical	Nominal Value	Unit	Test Method
Apparent Density	1.11	g/cm³	ASTM D1895
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	75		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	37.9	МРа	ASTM D638
Tensile Elongation (Yield)	15	%	ASTM D638
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
	Mix Ratio by Volume: 1.0		
Hardener	Mix Ratio by Weight: 1.0		
	Mix Ratio by Weight: 1.0		
Resin	Mix Ratio by Volume: 1.1		
Thermoset Mix Viscosity (25°C)	300	сР	ASTM D2393
	4300 to 5800		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

480 to 720

min

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2