

# CENUSIL® M 810 A/B

Silicone  
Wacker Chemie AG

Message:  
Silicone Rubber, RTV-2  
Mold Making, Mold Making  
Mold Making, Plastics and Rubber Processing

General Information			
Uses	Mold Making		
	Prototyping		
Uncured Properties	Nominal Value	Unit	Test Method
Color	White		
Curing Time	4.0	hr	
Pot Life	40	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	10		ISO 868
Tensile Strength	3.50	MPa	ISO 37
Tensile Elongation at Break	600	%	ISO 37
Tear Strength	15.0	kN/m	ASTM D624B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT