Eltex® LGB263N2070

High Density Polyethylene

INEOS Olefins & Polymers Europe

Message:

Eltex
LGB263N2070 high density polyethylene is a white compound manufactured by INEOS Polyolefins. It contains 5% titanium dioxide and is intended for the co-extrusion of bottles for the packaging of UHT sterilized milk.

The resin is specifically designed for 3- or 6- layer bottles. It guarantees the preservation of the organoleptic properties of milk and has the following essential properties:

High density, ensuring good rigidity of finished products

A melt viscosity which ensures easy processing

A very low odour level

It meets EU and FDA regulations governing the approval of materials used in the manufacture of packaging which may come into contact with food products.

| General Information | | | |
|---------------------------------------|--------------------------------------|----------|-----------------|
| Additive | Titanium Dioxide (TiO2) (5%) | | |
| Features | Food Contact Acceptable | | |
| | Good Organoleptic Properties | | |
| | Good Processability | | |
| | High Density | | |
| | Low to No Odor | | |
| | MedWide Molecular Weight Distrib. | | |
| | Medium Rigidity | | |
| | | | |
| Uses | Bottles | | |
| | Food Packaging | | |
| | | | |
| Agency Ratings | EU Food Contact, Unspecified Rating | | |
| | FDA Food Contact, Unspecified Rating | | |
| | | | |
| RoHS Compliance | Contact Manufacturer | | |
| Appearance | White | | |
| Processing Method | Coextrusion | | |
| Physical | Nominal Value | Unit | Test Method |
| Density ¹ | 1.00 | g/cm³ | ISO 1183/A |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 | | | |
| kg) | 0.70 | g/10 min | ISO 1133 |
| Viscosity ² (190°C) | 1200000 | mPa·s | Internal Method |
| NOTE | | | |
| | Compression molded discs, cooled | | |
| 1. | at 15°C per minute | | |

Apparent dynamic viscosity of the material extruded at 190°C through a 1.0 mm diameter and 15 mm long die, at apparent shear rate 100/s

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



2.