Shin-Etsu Elastomer KE-2095-60A/B

Silicone Rubber, HTV

Shin-Etsu Silicones of America

Message:

Shin-Etsu KE-2095-60 is a selective self-adhesive liquid injection molding silicone. It is supplied as two components which are mixed in a 1:1 ratio to ensure easy and accurate blending. The viscosity of KE-2095-60 is low enough to allow easy pumping through most injection molding systems. Selective self adhesion

Non adhesion to metals

Insert-molding and co-injection molding available

| General Information | | |
|--------------------------------|--------------------------------|-------|
| Features | Low viscosity | |
| | Workability, good | |
| | | |
| Agency Ratings | USP Class VI | |
| Processing Method | Liquid Injection Molding (LIM) | |
| Physical | Nominal Value | Unit |
| Specific Gravity | 1.11 | g/cm³ |
| Hardness | Nominal Value | Unit |
| Durometer Hardness | 60 | |
| Elastomers | Nominal Value | Unit |
| Tensile Strength | 8.30 | MPa |
| Tensile Elongation (Break) | 310 | % |
| Tear Strength ¹ | 35.0 | kN/m |
| Compression Set (180°C, 22 hr) | 10 | % |
| Thermoset | Nominal Value | Unit |
| Shelf Life (32°C) | 26 | wk |
| Additional Information | | |
| Press / Post Cure: Press | | |
| Uncured Properties | Nominal Value | Unit |
| Curing Time | 0.17 | hr |
| NOTE | | |
| 1. | B mould | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

