

Generic SMA

Styrene Maleic Anhydride

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic SMA
This information is provided for comparative purposes only.

General Information			
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.05 to 1.17	g/cm ³	ISO 1183
Apparent Density	0.60	g/cm ³	ASTM D1895
Melt Mass-Flow Rate (MFR) (240°C/10.0 kg)	20 to 22	g/10 min	ISO 1133
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	129 to 160	°C	DSC
Vicat Softening Temperature	110 to 160	°C	ISO 306

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT