

Polifil® PP GFPP-30

Polypropylene Homopolymer

The Plastics Group

Message:

Polifil® GFPP series compounds are homopolymer polypropylene resins reinforced with glass fibers. They provide high impact with increased strength, stiffness, surface hardness, and higher continuous temperature. Other benefits include reduced distortion under long-term stress. These compounds are used in appliances, electrical components, automotive, and utility products. Standard processing techniques are applicable. Use this information as a guide to aid you in selecting the proper resin for your application. TPG will custom compound and fine-tune our formulations for your application.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Dimensional Stability		
	Good Stiffness		
	High Hardness		
	High Impact Resistance		
	High Strength		
Uses	Homopolymer		
	Appliances		
	Automotive Applications		
	Electrical Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0 to 10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.30	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	96		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3590	MPa	ASTM D638
Tensile Strength (23°C)	49.0	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield, 23°C	3.0	%	
Break, 23°C	4.0	%	
Flexural Modulus - Tangent (23°C)	4270	MPa	ASTM D790
Flexural Strength (23°C)	72.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	64	J/m	ASTM D256

Gardner Impact (23°C, 12.7 mm)	0.452	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	154	°C	
1.8 MPa, Unannealed	143	°C	
Injection	Nominal Value	Unit	
Drying Temperature	82.2 to 104	°C	
Drying Time	1.0 to 2.0	hr	
Rear Temperature	210 to 221	°C	
Middle Temperature	216 to 227	°C	
Front Temperature	227 to 238	°C	
Nozzle Temperature	227 to 249	°C	
Processing (Melt) Temp	232 to 260	°C	
Mold Temperature	48.9 to 65.6	°C	
Injection Rate	Fast		
Back Pressure	0.172 to 0.517	MPa	
Screw Speed	30 to 60	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

