# Monprene® OM-10152

#### Thermoplastic Elastomer

## **Teknor Apex Company**

#### Message:

Monprene® OM-10152 is a Thermoplastic Elastomer (TPE) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Typical applications include:

Handles

Engineering/Industrial Parts

Adhesives/Tapes

Appliances

Business/Office Goods

General Information			
Uses	Appliances		
	Bonding		
	Cell Phones		
	Dental Applications		
	Flexible Grips		
	Handles		
	Knobs		
	Overmolding		
	Power/Other Tools		
	Sporting Goods		
	Toothbrush Handles		
	Writing Instruments		
Appearance	Opaque		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.908	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2			
kg)	0.20	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A <sup>1</sup>	45		
Shore A	54		
Shore A, 5 sec	52		
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	2.93	МРа	ASTM D412
Tensile Strength (Break)	4.83	MPa	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412

Additional Information	Nominal Value		
Adhesion to Nylon			
Injection	Nominal Value	Unit	
Drying Temperature	65.6	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	232 to 243	°C	
Middle Temperature	249 to 266	°C	
Front Temperature	254 to 271	°C	
Nozzle Temperature	266 to 277	°C	
Processing (Melt) Temp	221 to 243	°C	
Mold Temperature	23.9 to 60.0	°C	
Injection Pressure	1.38 to 6.89	МРа	
Injection Rate	Fast		
Back Pressure	0.172 to 0.862	МРа	
Screw Speed	50 to 120	rpm	
Cushion	3.81 to 25.4	mm	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Aged for 0 hr at 22°C

### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

1.

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

