

POCAN® C 1206 000000

Polycarbonate + PET

LANXESS Corporation

Message:

PET+PC, non-reinforced, injection molding, improved impact strength

General Information			
Features	Good Impact Resistance		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.22	g/cm ³	ISO 1183
Apparent Density	0.80	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	30.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow : 270°C, 2.00 mm ¹	0.70	%	
Across Flow : 120°C, 2 hr, 2.00 mm ²	0.30	%	
Flow : 270°C, 2.00 mm ³	0.70	%	
Flow : 120°C, 2 hr, 2.00 mm ⁴	0.30	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2200	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	50.0	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C)	4.5	%	ISO 527-2/50
Nominal Tensile Strain at Break (23°C)	10	%	ISO 527-2/50
Flexural Modulus ⁵ (23°C)	2200	MPa	ISO 178/A
Flexural Stress ⁶			
3.5% Strain	65.0	MPa	ISO 178/A
23°C	75.0	MPa	ISO 178
Flexural Strain at Flexural Strength ⁷ (23°C)	5.0	%	
ISO Shortname	PET+PC, GHMPR, 09-020		ISO 7792
Admissible Residence Time at Tmax	< 10.0	min	
Residual Moisture Content	0.0 to 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	20	kJ/m ²	
23°C	55	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Notched Izod Impact Strength			ISO 180/1A

-30°C	15	kJ/m ²	
23°C	50	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	120	°C	ISO 75-2/B
1.8 MPa, Unannealed	90.0	°C	ISO 75-2/A
Vicat Softening Temperature	130	°C	ISO 306/B120
Melting Temperature ⁸	250	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	9.0E-5	cm/cm/°C	
Transverse : 23 to 55°C	8.0E-5	cm/cm/°C	
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 to 8.0	hr	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	70.0 to 90.0	°C	
NOTE			
1.	60x60x2; WZ 80°C; 600 Bar		
2.	60x60x2		
3.	60x60x2; WZ 80°C; 600 Bar		
4.	60x60x2		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	Pull Rate: 2 mm/min; 50% RH		
8.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT