

Niuk 50RNG30

Polyamide 66

Shanghai Niuk New Plastic Technology Co., Ltd.

Message:

Niuk 50RNG30 is a Polyamide 66 (Nylon 66) material filled with 30% glass fiber. It is available in Asia Pacific.

Important attributes of Niuk 50RNG30 are:

Flame Rated

Flame Retardant

Corrosion Resistant

Creep Resistant

Good Toughness

Typical applications include:

Electrical/Electronic Applications

Wire & Cable

General Information	
Filler / Reinforcement	Glass Fiber,30% Filler by Weight
Additive	Flame Retardant
Features	Flame Retardant
	Good Corrosion Resistance
	Good Creep Resistance
	Good Wear Resistance
	Halogen Free
	High Heat Resistance
	High Rigidity
	Ultra High Toughness
Uses	Connectors
	Electrical/Electronic Applications
	Switches
	Wire & Cable Applications

Physical	Nominal Value	Unit	Test Method
Density	1.54	g/cm ³	ISO 1183
Molding Shrinkage - Across Flow ¹ (3.20 mm)	0.30 to 0.40	%	ISO 2577
Ash Content	30	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	150	MPa	ISO 527-2/50
Tensile Strain (Break)	3.0	%	ISO 527-2/50
Flexural Modulus ²	8000	MPa	ISO 178
Flexural Stress ³	240	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method


Charpy Notched Impact Strength (23°C)	8.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	30	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	230	°C	ISO 75-2/B
Vicat Softening Temperature	230	°C	ISO 306/B120
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	V-0		UL 94
NOTE			
1.	150x100x3.2 mm		
2.	2.0 mm/min		
3.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT