

SLOVALEN® PH 69 GF 20 T 10

Polypropylene

Plastcom

Message:

Modified homopolymer PP for injection moulding, chemically reinforced with 20% glass fibre and 10 % Talc, contains themodifier of mechanical properties.Increased strength in comparison with unfilled PP. Applied in all industry branches. Increased strength, toughness, modulus in tension due to themodification. Delivered in natural and in the full RAL colour scale.

| General Information | | | |
|---|----------------------------------|-------------------|-------------|
| Filler / Reinforcement | Glass Fiber,20% Filler by Weight | | |
| | Talc,10% Filler by Weight | | |
| Features | Chemically Coupled | | |
| | General Purpose | | |
| | Good Stiffness | | |
| | Good Strength | | |
| | Good Toughness | | |
| | Homopolymer | | |
| Uses | General Purpose | | |
| Appearance | Colors Available | | |
| | Natural Color | | |
| Processing Method | Injection Molding | | |
| Resin ID (ISO 1043) | PP | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.10 | g/cm ³ | ISO 1183 |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 5.0 | g/10 min | ISO 1133 |
| Molding Shrinkage | | | STM 64 0808 |
| Across Flow | 0.98 | % | |
| Flow | 0.62 | % | |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 5100 | MPa | ISO 527-2 |
| Tensile Stress (Yield) | 60.0 | MPa | ISO 527-2 |
| Tensile Strain (Yield) | 4.0 | % | ISO 527-2 |
| Flexural Modulus | 4550 | MPa | ISO 178 |
| Flexural Stress | 105 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength | | | ISO 179 |
| -20°C | 4.0 | kJ/m ² | |

| 23°C | 5.0 | kJ/m ² | |
|--|---------------|-------------------|----------------|
| Charpy Unnotched Impact Strength | | | ISO 179 |
| -20°C | 35 | kJ/m ² | |
| 23°C | 42 | kJ/m ² | |
| Thermal | Nominal Value | Unit | Test Method |
| Heat Deflection Temperature (0.45 MPa, Unannealed) | 118 | °C | ISO 75-2/B |
| Vicat Softening Temperature | 131 | °C | ISO 306/B |
| Melting Temperature (DSC) | 160 | °C | ISO 3146 |
| Flammability | Nominal Value | Unit | Test Method |
| Flame Rating | HB | | UL 94 |
| Glow Wire Ignition Temperature | 650 | °C | IEC 60695-2-13 |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 80.0 | °C | |
| Drying Time | 4.0 | hr | |
| Processing (Melt) Temp | 200 to 250 | °C | |
| Mold Temperature | 40.0 to 80.0 | °C | |
| Injection Pressure | 70.0 to 120 | MPa | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT