

IDI BMC Rosite 3550F

Thermoset, Unspecified

IDI Composites International

Message:

PRODUCT SERIES: Rosite 3000 SERIES BMC
PRODUCT DESCRIPTION: HIGH STRENGTH UL YELLOW CARD
These high strength BMC composites are suitable for use in electrical applications requiring materials that possesses dielectric properties and flammability performance from UL94 HB, V-0 & 5VA. These materials can be found in Underwriters Laboratory file E53587.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Flame Retardant		
	High Strength		
Uses	Electrical/Electronic Applications		
UL File Number	E53587		
Forms	BMC - Bulk Molding Compound		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.80	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.10	%	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	55.2 to 62.1	MPa	ASTM D638
Flexural Modulus	17200	MPa	ASTM D790
Flexural Strength	172	MPa	ASTM D790
Compressive Strength	159 to 172	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	530 to 640	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	204	°C	ASTM D648
Continuous Use Temperature	149	°C	ASTM D794
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.0E+14	ohms · cm	ASTM D257
Dielectric Strength ¹	12	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
60 Hz	5.15 to 5.35		
1 MHz	4.80 to 5.00		
Dissipation Factor			ASTM D150
1 kHz	0.017 to 0.019		
1 MHz	0.010 to 0.012		

Arc Resistance	170 to 185	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.05 mm)	V-0		UL 94
NOTE			
1.	Method A (Short-Time)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT