

ASACLEAN™ UB

Proprietary

ASACLEAN - Sun Plastech Inc.

Message:

PURGE COMPOUND FOR SCREW AND BARREL

Special grade to clean PE

Temperature range: 170°C - 320°C

ASACLEAN ® UB is especially designed to purge polyethylene. The fields of appliance are

Injection Moulding

Ideal for Blown Extrusion

It is characterized by the well known ASACLEAN ® purging power and efficiency. ASACLEAN ® UB is neither abrasive nor corrosive and is applicable for

Colour Changes

Material Changes

"Sealing"

Hot Runner Cleaning

Contact:

VELOX GmbH

Tel: +49 - (0)40 - 369 688 - 0

eMail: info@velox.com

Website: <http://www.velox.com>

General Information	
Features	Non-Corrosive
Uses	Purging Compound
Forms	Pellets
Processing Method	Extrusion Blow Molding Injection Molding

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.15	g/10 min	ISO 1133

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT