

# AEI SX559:CM540U

Crosslinked Polyethylene

AEI Compounds Limited

## Message:

Low-smoke, low-toxicity, halogen-free, flame-retardant, silane crosslinkable compound for low voltage insulation and sheathing of all types of cable. This is a low smoke, low fume, fire retardant silane crosslinkable compound which can be processed as a thermoplastic at high output rates and cured post processing by exposure to moisture. The graft component SX559 is mixed with a crosslinking catalyst masterbatch CM540U generally in the ratio 95:5. The compound combines good mechanical, electrical and fire retardant properties to meet demanding insulation specifications including BS7211. The compound can also be used for sheathing of cables requiring high fire retardance.

General Information			
Additive	Flame retardancy		
Features	Irritant gas low to no		
	Low smoke		
	Low toxicity		
	Crosslinkable		
	Halogen-free		
Uses	Flame retardancy		
	Flame Retardant Insulation		
	Flame Retardant Jacketing		
	Low voltage insulation		
	Cable sheath		
Agency Ratings	Wire and cable applications		
	BS 7211		
RoHS Compliance	EC 1907/2006 (REACH)		
	RoHS compliance		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.49	g/cm <sup>3</sup>	BS 2782 620A
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.5	g/10 min	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	14.0	MPa	IEC 60811-1-1
Tensile Strain (Break)	170	%	IEC 60811-1-1
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength (135°C, 168 hr)	20	%	IEC 60811-1-2

Change in Tensile Strain at Break (135°C, 168 hr)	-15	%	IEC 60811-1-2
Thermal	Nominal Value	Unit	Test Method
Deformation (100°C)	40	%	IEC 60811-3-1
Cold bending (-30°C)	pass		IEC 60811-1-4
Thermoset <sup>1</sup>			IEC 60811-2-1
Elongation under load, 20N/cm <sup>2</sup> : 200°C	30	%	IEC 60811-2-1
Permanent elongation after cooling	0.0	%	IEC 60811-2-1
Temperature index	> 300	°C	ISO 4589-3
Insulation Constant - Ki			IEC 60502
20°C	1.3E+12	ohms·cm	IEC 60502
90°C	5.0E+8	ohms·cm	IEC 60502
Conduction rate-of gases	13.0	μS/cm	IEC 60754-2
Corrosive gases in flue gas-pH	4.60		IEC 60754-2
Smoke Density		%	ASTM D2843
Halogen Acid Gas Evolution		%	IEC 60754-1
Head Temperature	190	°C	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	36	%	ISO 4589-2
Additional Information	Nominal Value	Unit	Test Method
Crosslinking & cure: A satisfactory cure can be obtained either by immersion in hot water or exposure to low pressure steam at a temperature up to 65°C			
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	130	°C	
Cylinder Zone 2 Temp.	150	°C	
Cylinder Zone 3 Temp.	170	°C	
Cylinder Zone 4 Temp.	180	°C	
Die Temperature	190	°C	
Extrusion instructions			
Many modern thermoplastic extruders will process the material although a screw designed to give good homogenisation without excessive shear (which could cause unacceptable increases in melt temperature) should be used. An extruder with an L/D ratio (length/diameter) of 15-24 and an extruder screw with a compression ratio 1.2:1 are recommended.			
NOTE			

1. Cure assessment by hot set test  
(forced cured at 80°C in water)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

**Susheng Import & Export Trading Co.,Ltd.**

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

