

Lucky Enpla LPC100F

Polycarbonate
Lucky Enpla Co LTD

Message:

Lucky Enpla LPC100F is a polycarbonate (PC) product. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. Lucky Enpla LPC100F applications include electrical/electronic applications and housing.

Features include:

flame retardant/rated flame

Halogen-free

General Information			
UL YellowCard	E217401-528917	E217401-101474743	E217401-100426424
Features	Halogen-free		
Uses	Electrical/Electronic Applications		
	Electrical housing		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 - 0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	61.8	MPa	ASTM D638
Flexural Modulus ²	2450	MPa	ASTM D790
Flexural Strength ³	96.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (3.18 mm)	690	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	121	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating (0.800 mm)	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	70.0 - 90.0	°C	
Drying Time	2.0 - 3.0	hr	
Rear Temperature	260 - 280	°C	
Middle Temperature	270 - 290	°C	
Front Temperature	270 - 290	°C	
Nozzle Temperature	270 - 290	°C	
Mold Temperature	60.0 - 80.0	°C	
Back Pressure	1.96 - 3.92	MPa	
Screw Speed	60 - 80	rpm	
Injection instructions			

Resin Temperature: 280-300°C Injection Pressure (1st Pressure): 700-1200 kg/cm² Injection Pressure (2nd Pressure): 400-800 kg/cm²

NOTE

1.	30 mm/min
2.	30 mm/min
3.	30 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

