

ResMart Ultra TPU 95A ES

Thermoplastic Polyurethane Elastomer (Polyester)

ResMart

Message:

Polyester based TPU Shore 95A hardness for injection molding or extrusion applications

General Information			
Agency Ratings	FDA Unspecified Rating		
RoHS Compliance	RoHS Compliant		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	95		
Shore D	55		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	37.9	MPa	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tensile Elongation (Break)	400	%	ASTM D412
Tear Strength	120	kN/m	ASTM D624
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	82.2 to 104	°C	
Drying Time - Desiccant Dryer	2.0 to 4.0	hr	
Suggested Max Moisture	0.010	%	
Processing (Melt) Temp	185 to 210	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT