

Polytech & Net 6200B

High Density Polyethylene

Polytech & Net Gmbh

Message:

Suitable for bottle (small) and household product. (shampoo, bleach, makeup)

General Information			
Uses	Bottles		
	Cosmetics		
Physical	Nominal Value	Unit	Test Method
Density	0.958	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.35	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (F50)	400	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	55		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	27.5	MPa	ASTM D638
Tensile Elongation (Break)	> 500	%	ASTM D638
Flexural Modulus	1320	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -80.0	°C	ASTM D746
Vicat Softening Temperature	123	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 1342475533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT