

HiFill® PA6/6 GF13 L YAG

Polyamide 66

Techmer Engineered Solutions

Message:

HiFill® PA6/6 GF13 L YAG is a polyamide 66 (nylon 66) product, which contains a 13% glass fiber reinforced material. It can be processed by injection molding and is available in North America. The main characteristics are: lubrication.

| General Information | | | |
|-------------------------------------|---|-------------------|-------------|
| Filler / Reinforcement | Glass fiber reinforced material, 13% filler by weight | | |
| Additive | Lubricant | | |
| Features | Laser marking | | |
| | Lubrication | | |
| Appearance | Available colors | | |
| Forms | Particle | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.23 | g/cm ³ | ASTM D792 |
| Molding Shrinkage - Flow (3.18 mm) | 0.60 | % | ASTM D955 |
| Water Absorption (24 hr) | 1.8 | % | ASTM D570 |
| Hardness | Nominal Value | Unit | Test Method |
| Rockwell Hardness (R-Scale) | 115 | | ASTM D785 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 112 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 3.0 | % | ASTM D638 |
| Flexural Modulus | 4830 | MPa | ASTM D790 |
| Flexural Strength | 174 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C, 3.18 mm) | 75 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load | | | ASTM D648 |
| 0.45 MPa, not annealed | 252 | °C | ASTM D648 |
| 1.8 MPa, not annealed | 221 | °C | ASTM D648 |
| CLTE - Flow | 3.2E-5 | cm/cm/°C | ASTM D696 |
| Electrical | Nominal Value | Unit | Test Method |
| Volume Resistivity | 1.0E+15 | ohms · cm | ASTM D257 |
| Dielectric Strength ¹ | 19 | kV/mm | ASTM D149 |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 82.2 | °C | |
| Drying Time | 2.0 - 4.0 | hr | |

| | | |
|------------------------|---------------|-----|
| Suggested Max Moisture | 0.12 | % |
| Rear Temperature | 282 - 293 | °C |
| Middle Temperature | 288 - 299 | °C |
| Front Temperature | 277 - 288 | °C |
| Nozzle Temperature | 282 - 293 | °C |
| Processing (Melt) Temp | 282 - 304 | °C |
| Mold Temperature | 54.4 - 93.3 | °C |
| Injection Rate | Moderate-Fast | |
| Back Pressure | 0.345 - 0.689 | MPa |

Injection instructions

Screw Speed: MediumRecommendations for Molding and Tool Conditions: Well ventedMoisture Content, as received: Product is packaged at 0.2% or less.Recomended Max Moisture: 0.12% down to 0.08%

NOTE


- Method A (short time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT