

BESTNYL SE35VI02AU

Polyamide 66

Triesa Plastics

Message:

Polyamide 6.6 black with 35% glass fibre reinforcement, stabilized against ultra violet rays (UV), regularly used in automotive industry in final pieces that require UV rays stability and good mechanical properties.

General Information			
Filler / Reinforcement	Glass Fiber,35% Filler by Weight		
Additive	UV Stabilizer		
Features	Good UV Resistance		
Uses	Automotive Applications		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Molding Shrinkage	0.50	%	ISO 294-4
Water Absorption (23°C, 24 hr)	0.70	%	ISO 62
Ash Content	35	%	Internal Method
Humidity - Pellets	0.20	%	ISO 1110
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	81		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10200	MPa	ISO 527-2
Tensile Stress	175	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	12	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	250	°C	ISO 75-2/B
Vicat Softening Temperature	> 260	°C	ISO 306
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Electric Strength	34	kV/mm	IEC 60243-1
Comparative Tracking Index	450	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 100	mm/min	FMVSS 302
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	100	°C
Drying Time	3.0 to 5.0	hr
Processing (Melt) Temp	275 to 290	°C
Mold Temperature	90.0 to 100	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

