## COPYLENE® CR350CS-01

## Polypropylene Random Copolymer

Phillips 66

## Message:

COPYLENE® CR350CS-01 is a clarified, reactor grade, random copolymer specially designed for clear injection molding applications and is formulated with lube for excellent mold release for larger articles.

Potential Applications:

Injection Molding

General Information			
Additive	Clarifier		
	Lubricant		
Features	Good Mold Release		
	High Clarity		
	Lubricated		
	Random Copolymer		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.902	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	35	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	29.3	MPa	ASTM D638
Tensile Elongation (Yield)	14	%	ASTM D638
Flexural Modulus - 1% Secant <sup>2</sup>	1070	МРа	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	74.0	°C	ASTM D648
NOTE			
1.	50 mm/min		
2.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

