DuraGrip® DGR 6290CL

Thermoplastic Elastomer

Advanced Polymer Alloys

accordance with ISO 2781.

NOTE

Message:

DuraGrip® 6290CL is a Thermoplastic Elastomer (TPE) designed for injection molding and extrusion processes. DuraGrip® 6290CL has excellent clarity, soft-touch feel, a high coefficient of friction, and bonds well to polypropylene. DuraGrip® 6290CL is also FDA compliant pursuant to 21 C.F.R. 177.2600. DuraGrip® 6290CL is not hygroscopic and under normal conditions does not require drying.

General Information			
Features	High Friction		
	Good adhesion		
	Definition, high		
A D.:	ELL 2002 (05 (EG (AMEEE)		
Agency Ratings	EU 2002/96/EC (WEEE)		
	FDA 21 CFR 177.2600		
RoHS Compliance	RoHS compliance		
Appearance	Clear/transparent		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.883	g/cm³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16	37	g/10 min	ASTM D1238
kg) Hardness	Nominal Value	Unit	Test Method
naruness	89	Offic	
Duramatar Hardness (Chara A. F.sas)			ASTM D2240, ISO 868
Durometer Hardness (Shore A, 5 sec)		11-14	Took Madhaad
Elastomers	Nominal Value	Unit	Test Method
Elastomers Tensile Stress	Nominal Value		ASTM D412, ISO 37
Elastomers Tensile Stress 100% strain	Nominal Value 6.69	МРа	ASTM D412, ISO 37 ASTM D412, ISO 37
Elastomers Tensile Stress 100% strain 300% strain	Nominal Value 6.69 7.65	MPa MPa	ASTM D412, ISO 37 ASTM D412, ISO 37 ASTM D412, ISO 37
Elastomers Tensile Stress 100% strain 300% strain Tensile Strength (Yield)	Nominal Value 6.69 7.65 9.45	MPa MPa MPa	ASTM D412, ISO 37 ASTM D412, ISO 37 ASTM D412, ISO 37 ASTM D412, ISO 37
Elastomers Tensile Stress 100% strain 300% strain Tensile Strength (Yield) Tensile Elongation (Break)	Nominal Value 6.69 7.65 9.45 410	MPa MPa MPa %	ASTM D412, ISO 37
Elastomers Tensile Stress 100% strain 300% strain Tensile Strength (Yield) Tensile Elongation (Break)	Nominal Value 6.69 7.65 9.45	MPa MPa MPa	ASTM D412, ISO 37 ASTM D412, ISO 37 ASTM D412, ISO 37 ASTM D412, ISO 37
Elastomers Tensile Stress 100% strain	Nominal Value 6.69 7.65 9.45 410	MPa MPa MPa %	ASTM D412, ISO 37

Page 1

1. C mould

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

