

ISPLEN® PP 010 X6E

Polypropylene Homopolymer

REPSOL

Message:

ISPLEN® PP-010 X6E is a homopolymer with a high molecular weight that contains a high thermal stability formulation. Due to averagely good flow properties and very high mechanical properties is a suitable grade to be processed into pipes

ADDITIVATION

ISPLEN® PP-010 X6E contains stabilizers and additives according to the end-use of the item in order to reinforce the thermal stability and increase the hot-water extraction resistance. Other additives may be included by the processor. Formulation allows polymer stability during the normal conditions of processing and use.

COLOURING

ISPLEN grades are supplied in natural colour but they can be easily coloured with pigments steady at processing temperatures, using dry -colouring or masterbatch techniques.

FOODSTUFF REGULATIONS

ISPLEN® PP-010 X6E are approved for food contact under certain legislation. For more information about specific country regulation, please, contact with our local representative or the Technical Service.

General Information			
Additive	Heat Stabilizer		
Features	Food Contact Acceptable		
	Good Colorability		
	Good Flow		
	Good Thermal Stability		
	Heat Stabilized		
	High Molecular Weight		
Uses	Industrial Applications		
	Piping		
Appearance	Natural Color		
Processing Method	Extrusion		
	Pipe Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.903	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/5.0 kg	0.55	g/10 min	
230°C/2.16 kg	0.28	g/10 min	
230°C/5.0 kg	1.0	g/10 min	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness	84		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	34.0	MPa	ISO 527-2
Tensile Strain (Yield)	14	%	ISO 527-2

Flexural Modulus	1200	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	8.5	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	92.0	°C	ISO 75-2/B
Vicat Softening Temperature	150	°C	ISO 306/A
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	190 to 200	°C	
Cylinder Zone 2 Temp.	190 to 205	°C	
Cylinder Zone 3 Temp.	195 to 210	°C	
Cylinder Zone 4 Temp.	195 to 215	°C	
Cylinder Zone 5 Temp.	200 to 220	°C	
Melt Temperature	205 to 225	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

