

CERTENE™ HPB-0354A

High Density Polyethylene
Muehlstein

Message:

HPB-0354A is a certified prime Phillips Process blow molding copolymer designed to meet end-use requirements of containers for packaging of Household Industrial Chemicals (HIC). HPB-0354A contains antistatic and features medium swell, easy and consistent processability in conventional continuous or intermittent extrusion equipment, and excellent balance of bottle ESCR, Impact strength and Stiffness. Applications include medium size containers for detergents, bleach, antifreeze, motor oil and ice chests. HPB-0354A recommended processing temperature is 160 to 180°C, with mold at 10 to 30°C.

General Information			
Additive	Antistatic property		
Features	Rigidity, high		
	High ESCR (Stress Cracking Resistance)		
	High density		
	Copolymer		
	Antistatic property		
	Impact resistance, high		
	Workability, good		
	Good chemical resistance		
Uses	Detergent resistance		
Forms	Packaging		
	Industrial container		
Processing Method			
	Blow molding		
Physical	Nominal Value	Unit	Test Method
Density	0.954	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.35	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, 100% Igepal, Compression Molded, F50)	50.0	hr	ASTM D1693
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, Compression Molded)	26.9	MPa	ASTM D638
Tensile Elongation ² (Break, Compression Molded)	700	%	ASTM D638
Flexural Modulus - 1% Secant ³ (Compression Molded)	1170	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Tensile Impact Strength (Compression Molded)	206	kJ/m ²	ASTM D1822

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	74.0	°C	ASTM D648
Brittleness Temperature	-90.0	°C	ASTM D746
Vicat Softening Temperature	127	°C	ASTM D1525

Additional Information

This Specimen was compression molded and was tested according to ASTM D1928 Procedure C.

Injection	Nominal Value	Unit
Mold Temperature	10.0 - 30.0	°C
Extrusion	Nominal Value	Unit
Melt Temperature	160 - 180	°C

NOTE

1. 50 mm/min
2. 50 mm/min
3. 1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

