

AZDEL™ SM10380

Polypropylene

Azdel, Inc.

Message:

AZDEL SM10380 is a glass mat thermoplastic laminate based upon random oriented continuous fiber mat contained within polypropylene resin matrix. This composite material features high flow properties and a very homogeneous fiber distribution. This material is typically used for standard semi-structural applications and where high impact and stiffness are desired, and is usually used in sheet form (un-molded) in applications such as large-truck trailer scuff liners.

General Information			
Filler / Reinforcement	Long glass fiber, 38% filler by weight		
Appearance	Black		
Forms	Sheet		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.17	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5140	MPa	ISO 527-2
Tensile Stress (Yield)	79.0	MPa	ISO 527-2
Tensile Strain (Break)	2.6	%	ISO 527-2
Flexural Modulus	5140	MPa	ISO 178
Flexural Stress	140	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Instrumented Dart Impact (4.00 mm, Total Energy)	23.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	154	°C	ASTM D648
CLTE - Flow (-40 to 121°C)	2.3E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Burning Rate	5.3	mm/min	ISO 3795
Additional Information			
Basis Weight, Internal Test Method: 0.67 lbs/ft ² Filler Content by Weight(ashing), Internal Test Method: 38 %Notched Izod Impact, ISO 180, 23°C, 4mm: 771 J/mSheet Thickness, Internal Test Method: 108 milsSpecific Gravity, ASTM D792, Laminated: 1.17			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

