# Sipolprene® 25170 B

### Thermoplastic Copolyester Elastomer

SIPOL S.p.A

#### Message:

Sipolprene® 25170 B (black color version in dry blend) is an ether ester thermoplastic elastomer (TPC-ET), developed and manufactured by Sipol, with a nominal hardness of Shore D 27, a very low modulus, and a rheological behaviour, which makes it suitable for injection molding and extrusion processing.

General Information				
Appearance	Black			
Processing Method	Extrusion			
	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.10	g/cm³	ASTM D792, ISO 1183	
Melt Mass-Flow Rate (MFR) (200°C/2.16				
kg)	12	g/10 min	ASTM D1238, ISO 1133	
Water Absorption <sup>1</sup> (23°C, 24 hr)	0.76	%	Internal Method	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore D)	27		ASTM D2240, ISO 868	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	23.0	MPa	ASTM D638, ISO 527-2	
Tensile Elongation (Break)	800	%	ASTM D638, ISO 527-2	
Flexural Modulus	30.0	MPa	ASTM D790, ISO 178	
Abrasion Resistance	42.0	mm³	DIN 53516	
Elastomers	Nominal Value	Unit	Test Method	
Tear Strength	85.0	kN/m	ASTM D1004	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (23°C)	No Break		ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
			ISO 306/A50, ASTM D1525 2	
Vicat Softening Temperature	73.0	°C	۷	
Peak Melting Temperature	173	°C	ASTM D3418, ISO 3146	
NOTE				
1.	Immersion			
2.	Rate A (50°C/h), Loading 1 (1	Rate A (50°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

