

Petrothene® NA940094

Low Density Polyethylene

LyondellBasell Industries

Message:

Petrothene NA940 is a series of resins used for heavy duty film applications. Excellent puncture resistance combined with impact properties make NA940 an exceptional choice when selected by customers for bags used to package fertilizer, peat moss, decorative stone and agricultural and construction materials. NA940 also has excellent heat shrink properties.

General Information	
Additive	Anti-caking agent (4000 ppm) Sliding agent (500 ppm)
Features	Low smoothness High caking resistance Perforation resistance Impact resistance, good Good heat sealability Compliance of Food Exposure
Uses	Films Bags
Agency Ratings	FDA 21 CFR 177.1520
Forms	Particle
Processing Method	Film extrusion Blow film

Physical	Nominal Value	Unit	Test Method
Density	0.918	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.25	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (100% Igepal, F0)	168	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	50		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	14.5	MPa	ASTM D638
Tensile Elongation (Break)	> 600	%	ASTM D638
Flexural Modulus	234	MPa	ASTM D790
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	51	µm	

secant modulus			ASTM D882
1% secant, MD: 51 μm	165	MPa	ASTM D882
1% secant, TD: 51 μm	186	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield, 51 μm	20.7	MPa	ASTM D882
TD: Yield, 51 μm	19.3	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture, 51 μm	300	%	ASTM D882
TD: Fracture, 51 μm	500	%	ASTM D882
Dart Drop Impact (51 μm)	220	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD : 51 μm	220	g	ASTM D1922
TD : 51 μm	200	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -76.0	°C	ASTM D746
Vicat Softening Temperature	90.0	°C	ASTM D1525
Extrusion	Nominal Value	Unit	
Melt Temperature	166 - 221	°C	
Extrusion instructions			

NA 940 has been designed for excellent processability, bubble stability and good heat sealing over a wide range of extrusion conditions. Optimum properties are found at melt temperatures of 330°-430°F (165°-221°C) and blow-up ratios between 1.8:1 and 2.5:1. Drawdown to 1.5 mil (38.1 microns) is possible at commercial rates when proper extrusion techniques are used.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

