

# Andur M-95 AS

Polyurethane (MDI)  
Anderson Development Company

### Message:

Andur M-95 AS is a custom formulated MDI based polyurethane elastomer system. It is designed as a low cost, easily processed candidate for use in dunnage applications. M-95 AS is a two component, 1:1 ratio (weight) system that can be processed at room temperature and yields a 95 Shore A elastomer. The system needs no post cure and contains no TDI.


General Information			
Features	Workability, good		
Forms	Liquid		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm <sup>3</sup>	ASTM D792
Thermoset	Nominal Value	Unit	Test Method
Pot Life	45	min	
Thermoset Mix Viscosity (21°C)	770	cP	ASTM D2393
Demold Time	6.0 - 8.0	min	
Additional Information			
Specific Gravity, ASTM D792, 70°F: 1.22 g/ml			
Injection	Nominal Value	Unit	
Mold Temperature	65.6 - 85.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT