

RTP ESD A 2580 FR

Polycarbonate + ABS

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
ESD 2580 FR Series is a polycarbonate/ABS alloy with carbon fibers added for electrical conductivity. These materials have excellent static dissipation characteristics, meet the flammability requirements of UL94 V-0, are non-sloughing and are available i

General Information			
Filler / Reinforcement	Carbon fiber reinforced material		
Additive	Flame retardancy		
Features	Conductivity		
	Electrostatic discharge protection		
	Antistatic property		
	No shedding		
	Flame retardancy		
Agency Ratings	MIL B-81705C		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.10 - 0.20	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7930	MPa	ASTM D638
Tensile Strength	117	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	6890	MPa	ASTM D790
Flexural Strength	165	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	110	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	480	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed)	107	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.59 mm, RTP Tested)	V-0		UL 94

Additional Information

Volume Resistivity, ASTM D257: 10E3 -10E9 ohm-cmSurface Resistivity, ASTM D257: 10E6 -10E12 ohm/sqStatic Decay, FTMS-4046.1, Mil B-81705C: <2.0 seconds

Injection	Nominal Value	Unit
Rear Temperature	232 - 288	°C
Middle Temperature	232 - 288	°C
Front Temperature	232 - 288	°C
Mold Temperature	71.1 - 98.9	°C
Injection Pressure	68.9 - 103	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT