# Hostacom TRC 352NA 95T CORNSILK

### Thermoplastic Polyolefin Elastomer

#### LyondellBasell Industries

#### Message:

Hostacom TRC 352NA 95T CORNSILK high melt flow, high flexural modulus, mineral-filled thermoplastic elastomeric olefin (TEO) resin has excellent impact/stiffness balance, good flowability properties, and excellent scratch resistance. It has an outstanding blooming resistance at elevated temperatures. It is typically used for interior automotive applications.

For regulatory compliance information, see Hostacom TRC 352NA 95T CORNSILK Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

General Information			
Filler / Reinforcement	Mineral filler		
Features	Rigidity, high		
	Rigid, good		
	Impact resistance, good		
	High liquidity		
	Scratch resistance		
Uses	Application in Automobile Field		
	Car interior parts		
	Car dashboard		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.05	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	18	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	20.0	MPa	ISO 527-2/50
Flexural Modulus - Chord <sup>1</sup> (23°C)	1850	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	4.5	kJ/m²	ISO 179/1eA
23°C	35	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

