

EnCom F0 ABS 6030

Acrylonitrile Butadiene Styrene

EnCom, Inc.

Message:

Flame Retardant ABS

General Information	
Features	Flame Retardant
Uses	Business Equipment
	Electrical/Electronic Applications
Appearance	Black
	Colors Available
	Natural Color
Forms	Pellets
Processing Method	Injection Molding
	Profile Extrusion

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.40 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	36.5	MPa	ASTM D638
Flexural Modulus	2240	MPa	ASTM D790
Flexural Strength (Yield)	64.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	75.6	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.57 mm	V-0		
3.18 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	76.7 to 87.8	°C	
Drying Time	2.0 to 4.0	hr	
Drying Time, Maximum	7.0	hr	

Suggested Max Moisture	0.15	%
Rear Temperature	149 to 182	°C
Middle Temperature	177 to 204	°C
Front Temperature	191 to 232	°C
Nozzle Temperature	191 to 232	°C
Processing (Melt) Temp	191 to 232	°C
Mold Temperature	48.9 to 76.7	°C
Back Pressure	0.172 to 0.689	MPa
Screw Speed	25 to 75	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

