

Bormed™ RF825MO

Polypropylene Random Copolymer

Borealis AG

Message:

Bormed RF825MO is a specially modified transparent polypropylene random copolymer with high meltflow. This polymer grade is intended for production of medical and medical-related articles. It is characterized by easy processability, high transparency, high gloss and good stiffness-impact balance. In addition it can be sterilized with ethylene oxide or steam and has an excellent chemical resistance. In addition to its good physical properties and excellent transparency, this grade also yields products with good printability.

General Information			
Features	Ethylene Oxide Sterilizable		
	Excellent Printability		
	Good Chemical Resistance		
	Good Impact Resistance		
	Good Processability		
	Good Stiffness		
	High Clarity		
	High Flow		
	High Gloss		
	Random Copolymer		
	Recyclable Material		
	Steam Sterilizable		
Uses	Caps		
	Closures		
	Disposable Hospital Goods		
	Labware		
	Medical/Healthcare Applications		
	Pharmaceuticals		
	Tubing		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ISO 1133
Molding Shrinkage	1.0 to 2.0	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	90		ISO 2039-2

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1150	MPa	ISO 527-2/1
Tensile Stress (Yield)	28.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	12	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹ (0.45 MPa, Unannealed)	80.0	°C	ISO 75-2/B
Injection	Nominal Value	Unit	
Processing (Melt) Temp	220 to 250	°C	
Mold Temperature	30.0 to 40.0	°C	
Injection Rate	Moderate-Fast		
Holding Pressure	20.0 to 50.0	MPa	
NOTE			

1. Injection molded specimen

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT