

Durethan® AKV 30 G H2.0 SR1 900051

Polyamide 66

LANXESS GmbH

Message:

PA 66, 30 % glass fibers, injection molding, heat-aging stabilized, improved surface finish

General Information				
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight			
Additive	heat stabilizer			
Features	Good heat aging resistance			
	Excellent appearance			
Agency Ratings	EC 1907/2006 (REACH)			
Processing Method	Injection molding			
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.36	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				
Vertical flow direction: 280°C, 3.00mm ¹	0.94	--	%	ISO 2577
Vertical flow direction: 120°C, 2 hours, 3.00mm ²	0.080	--	%	ISO 294-4
Flow direction: 280°C, 3.00mm ³	0.25	--	%	ISO 2577
Flow direction: 120°C, 2 hours, 3.00mm ⁴	0.040	--	%	ISO 2577
Water Absorption				ISO 62
Saturated, 23°C	6.0	--	%	ISO 62
Equilibrium, 23°C, 50% RH	2.0	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	220	120	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9600	6500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	180	120	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	6.0	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	8400	5600	MPa	ISO 178/A
Flexural Stress ⁶				
3.5% strain	260	150	MPa	ISO 178/A
23°C	270	170	MPa	ISO 178
Flexural Strain at Flexural Strength ⁷ (23°C)	4.0	6.0	%	

Burning Behavior ⁸	passed	--		ISO 3795
ISO Shortname	PA 66, GHR, 14-100, GF30	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Films	Dry	Conditioned	Unit	Test Method
Film Puncture Energy				ISO 6603-2
-- ⁹	1.90	--	J	ISO 6603-2
-- ¹⁰	2.10	3.60	J	ISO 6603-2
Film Puncture Force				ISO 6603-2
-- ¹¹	680	--	N	ISO 6603-2
-- ¹²	740	920	N	ISO 6603-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-40°C	< 10	< 10	kJ/m ²	ISO 179/1eA
-30°C	< 10	< 10	kJ/m ²	ISO 179/1eA
23°C	10	15	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	60	60	kJ/m ²	ISO 179/1eU
23°C	70	75	kJ/m ²	ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	ISO 180/1A
23°C	< 10	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	50	50	kJ/m ²	ISO 180/1U
23°C	55	65	kJ/m ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	250	--	°C	ISO 75-2/B
1.8 MPa, not annealed	220	--	°C	ISO 75-2/A
8.0 MPa, not annealed	90.0	--	°C	ISO 75-2/C
Vicat Softening Temperature	> 230	--	°C	ISO 306/B50, ISO 306/B120
Melting Temperature ¹³	260	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	2.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	9.0E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+15	1.0E+13	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	1.0E+12	ohms · cm	IEC 60093

Dielectric Strength (23°C, 1.00 mm)	31	28	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
23°C, 100 Hz	4.00	8.00		IEC 60250
23°C, 1 MHz	4.00	4.00		IEC 60250
Dissipation Factor				IEC 60250
23°C, 100 Hz	9.0E-3	0.18		IEC 60250
23°C, 1 MHz	0.017	0.060		IEC 60250
Comparative Tracking Index (Solution A)	375	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.60 mm	HB	--		UL 94
3.20 mm	HB	--		UL 94
Glow Wire Flammability Index (2.00 mm)	650	--	°C	IEC 60695-2-12
Oxygen Index ¹⁴	26	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	280 - 300		°C	
Mold Temperature	80.0 - 120		°C	
NOTE				
1.	150x150x3; MT 80°C; 500 Bar			
2.	150x150x3			
3.	150x150x3; MT 80°C; 500 Bar			
4.	150x150x3			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	Pull Rate: 2 mm/min; 50% RH			
8.	US-FMVSS302			
9.	-30°C			
10.	23°C			
11.	-30°C			
12.	23°C			
13.	10°C/min			
14.	Procedure A			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT