Texalan® 5 Series 572D

Thermoplastic Polyurethane Elastomer (Polyester)

Austin Novel Materials Co. Ltd.

Message:

Texalan® 5 Series 572D is a Thermoplastic Polyurethane Elastomer (Polyester) (TPU-Polyester) material. It is available in Asia Pacific, Europe, or North America for blow molding, calendering, coextrusion, extrusion, or injection molding.

Important attributes of Texalan® 5 Series 572D are:

Chemical Resistant

High Strength

Impact Resistant

Low Temperature Resistant

Wear Resistant

| General Information | | | | |
|---------------------|--------------------------|-------|-------------|--|
| Features | Good Abrasion Resistance | | | |
| | High Elasticity | | | |
| | High Impact Resistance | | | |
| | High Tensile Strength | | | |
| | Low Temperature Resistan | t | | |
| | Oil Resistant | | | |
| | | | | |
| Processing Method | Blow Molding | | | |
| | Calendering | | | |
| | Coextrusion | | | |
| | Extrusion | | | |
| | Film Extrusion | | | |
| | Injection Molding | | | |
| | | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Density | 1.16 to 1.20 | g/cm³ | ISO 1183 | |

| Physical | Nominal Value | Unit | Test Method |
|--|------------------|------------|-------------|
| Density | 1.16 to 1.20 | g/cm³ | ISO 1183 |
| Hardness | Nominal Value | Unit | Test Method |
| Shore Hardness (Shore D) | 69 to 75 | | ISO 868 |
| Mechanical | Nominal Value | Unit | Test Method |
| Abrasion Resistance | < 40.0 | mm³ | ISO 4649 |
| Elastomers | Nominal Value | Unit | Test Method |
| | | | |
| Tensile Stress | | | ISO 37 |
| Tensile Stress 100% Strain | > 30.0 | MPa | ISO 37 |
| | > 30.0 > 48.0 | MPa MPa | ISO 37 |
| 100% Strain | | | ISO 37 |
| 100% Strain 300% Strain | > 48.0 | МРа | |
| 100% Strain 300% Strain Tensile Stress (Yield) | > 48.0 > 55.0 | MPa MPa | ISO 37 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

