

LubriOne™ NN-10GF/10T BLACK

Polyamide 66
PolyOne Corporation

Message:

LubriOne™ Lubricated and Wear-Resistant Compounds have been specifically formulated to be self-lubricating materials, offering low coefficient of friction and improved wear resistance properties. LubriOne compounds have been demonstrated to reduce friction, noise, vibration, heat buildup and improve product durability.

General Information			
UL YellowCard	E76261-101415440		
Features	Good Wear Resistance		
	Low Friction		
	Lubricated		
Uses	Appliance Components		
	Automotive Applications		
	Bearings		
	Business Equipment		
	Consumer Applications		
	Conveyor Parts		
	Gears		
	Industrial Applications		
	Printer Parts		
	Pulleys		
	Rollers		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.27	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6000	MPa	ISO 527-2
Tensile Stress (Break)	105	MPa	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact Strength	40	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	245	°C	ISO 75-2/B
1.8 MPa, Unannealed	245	°C	ISO 75-2/A
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 100	mm/min	ISO 3795

Flame Rating	HB	UL 94
Injection	Nominal Value	Unit
Processing (Melt) Temp	277 to 304	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

