

INELEC PCABSASTF10FR

Polycarbonate + ABS
Infinity LTL Engineered Compounds

Message:

INELEC PCABSASTF10FR is a Polycarbonate + ABS (PC+ABS) product. It is available in North America.
Characteristics include:
Flame Retardant
Antistatic
Lubricated

General Information			
Additive	Antistatic		
	Flame Retardant		
	PTFE Lubricant (10%)		
Features	Antistatic		
	Flame Retardant		
	Lubricated		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.60 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	37.9	MPa	ASTM D638
Tensile Elongation (Yield)	2.0 to 5.0	%	ASTM D638
Flexural Modulus	2070	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	130	J/m	ASTM D256
Unnotched Izod Impact	530 to 640	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	96.1	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+9 to 1.0E+11	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	93.3	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Processing (Melt) Temp	243 to 260	°C	
Mold Temperature	51.7 to 82.2	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	

Vent Depth	0.025 to 0.051	mm
------------	----------------	----

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

