

LIHAN® A9000N

Polyamide 66

Nanjing Lihan Chemical Co., Ltd.

Message:

LIHAN® A9000N is a Polyamide 66 (Nylon 66) product. It can be processed by injection molding and is available in Asia Pacific. Primary characteristic: flame rated.

General Information				
Forms		Pellets		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.15	--	g/cm ³	ISO 1183
Molding Shrinkage	1.0 to 1.4	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.90 to 1.3	--	%	ISO 62
Water Content	7.0 to 8.0	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	120	105		ISO 2039-2
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress (Break)	75.0	50.0	MPa	ISO 527-2
Tensile Strain (Break)	10	40	%	ISO 527-2
Flexural Modulus	2900	--	MPa	ISO 178
Flexural Stress	100	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact Strength	4.5	9.0	kJ/m ²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	215	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	80.0	--	°C	ISO 75-2/A
Melting Temperature	260	--	°C	DSC
CLTE - Flow	7.0E-5 to 1.0E-4	--	cm/cm/°C	ASTM D696
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	1.0E+10	ohms	ASTM D257
Dielectric Strength	17	--	kV/mm	ASTM D149
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.59 mm)	V-0	--		UL 94
Injection	Dry	Unit		
Processing (Melt) Temp	255 to 280		°C	
Mold Temperature	60.0 to 70.0		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

