

# HOPELEN FR-150H

Polypropylene Homopolymer  
Lotte Chemical Corporation

Message:

FR-150H is a low melt flow rate resin with a narrow molecular weight distribution homopolymer.  
It is ideally suited for woven & nonwoven application including staple fiber as well as continuous filament yarn and HTY(high tenacity fiber).  
It is formulated with an anti-gasfading stabilisation and weatherability(UV stabilizer agent) package

General Information			
Additive	Anti-gas fading		
	UV Stabilizer		
Features	Gas-fading Resistant		
	Homopolymer		
	Low Flow		
	Narrow Molecular Weight Distribution		
Uses	BCF Multifilaments		
	BCF Yarn		
	Filaments		
	Nonwovens		
	Staple Fibers		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	34.3	MPa	ASTM D638
Tensile Elongation (Break)	> 100	%	ASTM D638
Flexural Modulus	1470	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	20	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	109	°C	ASTM D648
Vicat Softening Temperature	152	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT