Silopren® LSR 3285/50

Silicone Rubber, LSR

Momentive Performance Materials Inc.

Message:

Silopren LSR 3285/50 is a two-component liquid silicone rubber for injection molding processes. This material is an excellent candidate to consider for the manufacture of elastomeric articles requiring self-lubricating properties. The self-lubricating effect is achieved by a fluid which exudes out of the vulcanizate over an extended period of time. It typically starts between a few hours and one day after vulcanization.

Key Features and Benefits

Vulcanizates consisting of Silopren LSR 3285/50 liquid silicone rubber are typically distinguished by the following properties:

self-lubricating properties transparent

low viscosity

fast cure

high thermal stability

outstanding resistance to aging

easy to color

Potential Applications

Because of the outstanding properties, Silopren LSR 3285/50 liquid silicone rubber is an excellent candidate to consider for use in wire harness applications for the following elastomeric articles:

cable seals

grommets

gaskets

plug seals

General Information										
Features	Fast Cure									
	Fast Molding Cycle									
	Good Colorability									
	Good Mold Release Good Thermal Stability Low Viscosity Self Lubricating									
						Uses	Gaskets			
							Grommets			
Seals										
Forms	Liquid									
Processing Method	Injection Molding									
Physical	Nominal Value	Unit	Test Method							
Density	1.13	g/cm³	DIN 53479							
Hardness	Nominal Value	Unit	Test Method							
Durometer Hardness (Shore A)	53		DIN 53505							
Elastomers	Nominal Value	Unit	Test Method							
Tensile Strength	10.9	MPa	DIN 53504							
Tensile Elongation (Break)	530	%	DIN 53504							
Tear Strength ¹	40.0	kN/m	ASTM D624							

Compression Set (175°C, 22 hr)	25	%	ISO 815
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Part A	Mix Ratio by Weight: 1.0		
Part B	Mix Ratio by Weight: 1.0		
Shelf Life (< 27°C)	77	wk	
Post Cure Time (200°C)	4.0	hr	
Additional Information	Nominal Value	Unit	Test Method
Vulcanization (175°C)	10.0	min	
Fluid Content			
2	2.0	%	
3	2.0	%	
Uncured Properties	Nominal Value	Unit	Test Method
Color			
4	White		
5	White		
Viscosity			DIN 53018
20°C ⁶	630	Pa·s	
20°C ⁷	680	Pa·s	
Pot Life (20°C)	4300	min	
NOTE			
1.	Die B		
2.	Part B		
3.	Part A		
4.	Part B		
5.	Part A		
6.	Part B		
7.	Part A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

