

HiFill® PET GF45 2000

Polyethylene Terephthalate

Techmer Engineered Solutions

Message:

HiFill® PET GF45 2000 is a Polyethylene Terephthalate (PET) product filled with 45% glass fiber. It can be processed by injection molding and is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber,45% Filler by Weight		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.69	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.20	%	ASTM D955
Water Absorption (24 hr)	0.035	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	121		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	190	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	13800	MPa	ASTM D790
Flexural Strength	283	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	227	°C	ASTM D648
Melting Temperature	254	°C	
CLTE - Flow	2.3E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength ¹	18	kV/mm	ASTM D149
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Rear Temperature	271 to 288	°C	
Middle Temperature	271 to 288	°C	
Front Temperature	271 to 288	°C	
Processing (Melt) Temp	274	°C	
Mold Temperature	93.3 to 110	°C	

Back Pressure	0.345 to 0.689	MPa
Screw Speed	30 to 60	rpm

NOTE

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

