## RapidCast™ RC-200

Polyurethane Thermoset Elastomer Innovative Polymers, Inc.

## Message:

RC-200 is a tough, impact resistant elastomer formulated for meter mix dispensing methods. Excellent physical properties can be obtained with a room temperature cure without the utilization of mercury, MOCA or TDI.

General Information				
Features	Good Toughness			
	High Impact Resistance			
RoHS Compliance	RoHS Compliant			
Appearance	Off-White			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity				
Cured	1.05	g/cm³		
Hardener	1.07	g/cm³		
Base Resin	1.20	g/cm³		
Molding Shrinkage - Flow	0.10 to 0.50	%	ASTM D2566	
Mechanical	Nominal Value	Unit	Test Method	
Flexural Modulus	1140	MPa	ASTM D790	
Flexural Strength	51.7	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact	140	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load (0.45 MPa, Unannealed)	65.0	°C	ASTM D648	
Thermoset	Nominal Value	Unit	Test Method	
Thermoset Components				
	Mix Ratio by Volume: 100			
Hardener	Mix Ratio by Weight: 89			
	Mix Ratio by Weight: 100			
Resin	Mix Ratio by Volume: 100			
Demold Time	10 to 20	min		
Uncured Properties	Nominal Value	Unit	Test Method	

25°C <sup>1</sup>	0.50	Pa·s		
25°C <sup>2</sup>	0.90	Pa·s		
25°C <sup>3</sup>	1.0	Pa·s		
Curing Time <sup>4</sup>	40	hr		
Gel Time	0.83 to 1.2	min		
Cured Properties	Nominal Value	Unit	Test Method	
Shore Hardness (Shore D)	75 to 85		ASTM D2240	
Tensile Modulus	1720	MPa	ASTM D638	
Tensile Strength	44.8	MPa	ASTM D638	
Tensile Elongation at Break	5.0	%	ASTM D638	
NOTE				
1.	Resin			
2.	Mixed			
3.	Hardener			
4.	24 hours at 77°F + 16 hours at 150°F			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

