

Bynel® 3860

Ethylene Vinyl Acetate Copolymer
DuPont Packaging & Industrial Polymers

Message:

BYNEL® Series 3800 resins are anhydride-modified ethylene vinyl acetate polymers. They are available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene (PE) resins.

General Information			
Agency Ratings	FDA 21 CFR 175.105		
Forms	Particle		
Processing Method	Co-extrusion molding Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.960	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.7	g/10 min	ASTM D1238, ISO 1133
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	48.0	°C	ASTM D1525, ISO 306
Melting Temperature	74.0	°C	DSC, ISO 3146
Freezing Point	52	°C	ASTM D3418
Additional Information			
The value listed as Melting Point, DSC, was tested in accordance with ASTM D3418.Freezing Point (DSC), ASTM D3418: 52°C			
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	135	°C	
Cylinder Zone 2 Temp.	185	°C	
Cylinder Zone 3 Temp.	235	°C	
Cylinder Zone 4 Temp.	235	°C	
Cylinder Zone 5 Temp.	235	°C	
Adapter Temperature	235	°C	
Melt Temperature	< 235	°C	
Die Temperature	235	°C	
Extrusion instructions			
Processing conditions shown are for coextrusion with EVOH.			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

