Adell Polyamide AJ-34

Polyamide 66

Adell Plastics, Inc.

Message:

Adell Polyamide AJ-34 is a Polyamide 66 (Nylon 66) material filled with 20% glass fiber. It is available in North America. Important attributes of Adell Polyamide AJ-34 are:

Flame Rated

Impact Resistant

Typical application of Adell Polyamide AJ-34: Automotive

| General Information | | | |
|-------------------------------------|----------------------------------|-------|-------------|
| Filler / Reinforcement | Glass Fiber,20% Filler by Weight | | |
| Features | High Impact Resistance | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.23 to 1.25 | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow | 0.40 to 0.70 | % | ASTM D955 |
| Water Absorption (24 hr) | 0.60 | % | ASTM D570 |
| Hardness | Nominal Value | Unit | Test Method |
| Rockwell Hardness | | | ASTM D785 |
| M-Scale | 85 | | |
| R-Scale | 119 | | |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 110 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 3.0 to 4.0 | % | ASTM D638 |
| Flexural Modulus | 5520 | MPa | ASTM D790 |
| Flexural Strength | 145 | MPa | ASTM D790 |
| Compressive Strength | 138 | MPa | ASTM D695 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C, 3.18 mm) | 180 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load | | | ASTM D648 |
| 0.45 MPa, Unannealed | 249 | °C | |
| 1.8 MPa, Unannealed | 238 | °C | |
| Melting Temperature | 249 to 260 | °C | ASTM D789 |
| Flammability | Nominal Value | | Test Method |
| Flame Rating | НВ | | UL 94 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

