

SEPAZ™ C140GP

Liquid Crystal Polymer

Mando Advanced Materials Co., Ltd.

Message:

SEPAZ™ C140GP is a Liquid Crystal Polymer (LCP) product filled with 40% glass fiber. It is available in Asia Pacific. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.71	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	135	MPa	ASTM D638
Tensile Elongation (Break)	1.3	%	ASTM D638
Flexural Modulus	15600	MPa	ASTM D790
Flexural Strength	182	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	78	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	271	°C	ASTM D648
Peak Melting Temperature	335	°C	ASTM D2133
Flammability	Nominal Value		Test Method
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	350 to 360	°C	
Mold Temperature	30.0 to 95.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT