

# YUPLENE® RX3700

Polypropylene Random Copolymer

SK Global Chemical

Message:

YUPLENE RX3700 is propylene random copolymer that is made for injection molding. It has excellent impact strength as well as excellent transparency. Since it has high fluidity and dimensional stability, it can be used for food packaging, packaging container and various home appliances. YUPLENE RX3700 is suitable for application which needs high impact strength such as cold chain system. YUPLENE RX3700 complies with FDA regulation 21 CFR 177.1520 for the exposure to food.

General Information			
Features	Good Dimensional Stability		
	Good Impact Resistance		
	High Flow		
	High Gloss		
	Random Copolymer		
Uses	Appliance Components		
	Containers		
	Food Containers		
	Food Packaging		
Agency Ratings	FDA 21 CFR 177.1520		
Appearance	Clear/Transparent		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ASTM D1238
Spiral Flow	> 80.0	cm	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	72		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	24.5	MPa	ASTM D638
Tensile Elongation (Break)	> 500	%	ASTM D638
Flexural Modulus	1080	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	130	J/m	ASTM D256
Aging	Nominal Value	Unit	Test Method
Oven Aging	15.0	day	ASTM D3012
Heat Deflection Temperature	80	°C	ASTM D648
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	125	°C	ASTM D1525

Optical	Nominal Value	Unit	Test Method
Haze	< 10	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

