

Forprene® 6NE901A75

Thermoplastic Vulcanizate

SO.F.TER. SPA

Message:

Forprene® 6NE901A75 is a thermoplastic vulcanized rubber (TPV) material. This product is available in North America, Latin America or Europe. The processing method is: extrusion. Forprene® The main characteristics of 6NE901A75 are: compliance with REACH standards.

General Information			
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Black		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.960	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	76		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Set	18	%	ASTM D412
Tensile Stress ¹ (100% Strain)	3.10	MPa	ASTM D412
Tensile Strength ²	7.50	MPa	ASTM D412
Tensile Elongation ³ (Break)	560	%	ASTM D412
Tear Strength ⁴	34.0	kN/m	ASTM D624
Compression Set ⁵ (70°C, 22 hr)	38	%	ASTM D395B
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Cylinder Zone 1 Temp.	170	°C	
Cylinder Zone 2 Temp.	180	°C	
Cylinder Zone 3 Temp.	185	°C	
Die Temperature	185	°C	
Extrusion instructions			
Extrusion Head Temperature: 195°C			
NOTE			
1.	Mouth die c		
2.	Mouth die c		
3.	Mouth die c		
4.	C mould		
5.	Type 1		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT