

VECTOR® 8550

Styrene Butadiene Styrene Block Copolymer
Dexco Polymers LP

Message:

VECTOR® 8550 is a Styrene Butadiene Styrene Block Copolymer (SBS) product. It can be processed by blow molding, extrusion, or injection molding and is available in North America. Typical application: Food Contact Applications. Primary characteristic: copolymer.

General Information	
Features	Copolymer
Agency Ratings	FDA Food Contact, Unspecified Rating
Forms	Pellets
Processing Method	Blow Molding
	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.938	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.2 to 1.4	%	ASTM D955

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	68		ASTM D2240

Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	4.83	MPa	ASTM D412
Tensile Strength (Yield)	31.0	MPa	ASTM D412
Tensile Elongation (Break)	900	%	ASTM D412

Injection	Nominal Value	Unit
Processing (Melt) Temp	149 to 204	°C
Mold Temperature	10.0 to 40.6	°C
Injection Pressure	34.5 to 138	MPa
Injection Rate	Slow-Moderate	
Back Pressure	0.345 to 0.689	MPa
Screw Speed	25 to 75	rpm
Clamp Tonnage	2.1 to 4.1	kN/cm ²
Screw Compression Ratio	2.0:1.0 to 3.0:1.0	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

