

Prime 4070 TRNS

Rigid Polyvinyl Chloride

Prime PVC®

Message:

High Impact Clear Profile Extrusion Grade.

General Information			
Features	High Impact Resistance		
Uses	Profiles		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	79		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2690	MPa	ASTM D638
Tensile Strength (Yield)	41.4	MPa	ASTM D638
Flexural Modulus	2550	MPa	ASTM D790
Flexural Strength (Yield)	82.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	960	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	71.1	°C	ASTM D648
CLTE - Flow	5.8E-5	cm/cm/°C	ASTM D696

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT